
$\mathsf{T} \equiv \mathsf{C} \vdash \mathsf{H} \perp \mathsf{I} \vdash \mathsf{T} \equiv | \mathsf{A} \subset \mathsf{O} \cup \mathsf{S} \top \mathsf{I} \subset \mathsf{S}^{\mathsf{T}}$

MINI WAVE PANELS | ACCENT SERIES



TECHLITE® Mini Wave Panels

TECHLITE® Mini Wave Panels provide maximum sound absorption for a wide range of applications. Available in a variety of thicknesses to suit your application, the curved geometry provides exceptional performance and visual interest. The TECHLITE® foam used to manufacture TECHLITE® Mini Wave Panels also has advantages such as being lightweight, easy to install, and providing comprehensive sound absorption, even at very high frequencies. TECHLITE® Mini Wave Panels offer design versatility and are able to be installed vertically or horizontally.

BENEFITS

Absorbs and reduces noise Very low-density / lightweight Excellent thermal properties Class A fire-rated (ASTM E 84) Easy to install

USES AND APPLICATIONS

Offices Lobbies Restaurants Entertainment facilities Libraries Religious facilities

SIZES/COLORS

12" x 48" x 2" or 18" x 48" x 2" Natural White Light Grey Other Color Options Available

PHYSICAL PROPERTIES

- Material Service Temp Density
- Fire Rating Finish

800.922.5252

FAX 480.894.6255

INFO@TECHLITE.COM TECHLITE.COM 2122 W 5TH PLACE TEMPE, AZ 85281

TECHLITE® Flexible Open-Cell Melamine Foam

-40°F to 350°F Light Grey 0.56 ± 0.09 lb/ft³

White 0.47 ± 0.13 lb/ft³

Class A per ASTM E 84

White or Light Grey

a beautifully sound decision"

$\mathsf{T} \equiv \mathsf{C} \vdash \mathsf{H} \sqcup \mathsf{T} \equiv | \mathsf{A} \subset \mathsf{O} \cup \mathsf{S} \top | \mathsf{C} \mathsf{S}^{\mathsf{M}}$

Sound Absorption Coefficient [Sabins / ft²]												
Finish		_								wounting type		
White	2.00	0.22	0.58	1.13	1.09	1.04	1.06	0.96	0.95	A		
Total Absorption [Sabins / Baffle]												
т	hicknoss						٨٥٥	arant	Annak	ont Mounting		

Finish	Thickness [in]	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	Apparent SAA*	Apparent NRC*	Mounting Type
White	2.00	0.61	1.93	5.02	8.34	9.22	9.45	1.51	1.50	J

Absorption results tested in accordance to ASTM C 423-09a

*Apparent SAA and NRC values are calculated using I face/baffle = 32.08 ft2/baffle.

800.922.5252 FAX 480.894.625 NFO@TECHLITE.COM TECHLITE.COM 122 W 5TH PLACE EMPE, AZ 85281

a beautifully sound decision™