TECHLITE ACOUSTICS

LARGE WAVE PANELS | ACCENT SERIES



TECHLITE® Large Wave Panels

TECHLITE® Large Wave Panels provide maximum sound absorption for a wide range of applications. Available in a variety of thicknesses to suit your application, the curved geometry provides exceptional performance and visual interest. The TECHLITE® foam used to manufacture TECHLITE® Large Wave Panels also has advantages such as being lightweight, easy to install, and providing comprehensive sound absorption, even at very high frequencies. TECHLITE® Large Wave Panels offer design versatility and are able to be installed vertically or horizontally.

PHYSICAL PROPERTIES							
Material	TECHLITE® Flexible Open-Cell Melamine Foam						
Service Temp	-40°F to 350°F						
Density	Light Grey 0.56 ± 0.09 lb/ft ³						
Delisity	White 0.47 ± 0.13 lb/ft ³						
Fire Rating	Class A per ASTM E 84						
Finish	White or Light Grey						

BENEFITS

Absorbs and reduces noise Very low-density / lightweight Excellent thermal properties Class A fire-rated (ASTM E 84) Easy to install

USES AND APPLICATIONS

Offices
Governmental facilities
Restaurants
Entertainment facilities
Transportation hubs
Religious facilities

SIZES/COLORS

48" x 96" panel with thicknesses of 2", 2 1/2" and 3" Natural White or Light Grey Other Color Options Available

$\textbf{T \equiv C \; H \; L \; I \; T \equiv | \; A \; C \; O \; U \; S \; T \; I \; C \; S^{\scriptscriptstyle \top}}$

Sound Absorption Coefficient [Sabins / ft²]											
Finish	Thickness [in]	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	SAA	NRC	Mounting Type	
White	2.00	0.15	0.46	1.01	0.98	1.02	1.04	0.89	0.85	А	
	2.50	0.28	0.69	1.19	1.06	1.09	1.07	1.00	1.00	Α	
	3.00	0.35	0.88	1.24	1.05	1.06	1.06	1.06	1.05	А	

Total Absorption [Sabins / Baffle]											
Finish	Thickness [in]	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	Apparent SAA*	Apparent NRC*	Mounting Type	
White	2.00	8.00	17.12	40.53	54.60	58.51	60.88	1.34	1.35	J	
	2.50	10.06	20.64	48.28	57.38	61.23	63.36	1.47	1.45	J	
	3.00	10.98	25.88	54.86	60.98	65.05	65.20	1.64	1.60	J	

Absorption results tested in accordance to ASTM C 423-09a

^{*}Apparent SAA and NRC values are calculated using I face/baffle = 32.08 ft2/baffle.